

Compound OK 99



| | |
|--|--|
| Properties | |
| Application | for voltages up to 1 kV |
| Basis | modified hydrocarbon resin (marking-free) |
| Mixing Ratio | 100 : 50 |
| After Hardening | soft-elastic, removable |
| Resin Compound | |
| Flash Point | > 200 °C |
| Viscosity (23°C) | app. 8.000 mPas |
| Hardener | |
| Flash Point | > 200 °C |
| Viscosity (23 °C) | app. 4.800 mPas |
| Reaction Compound | |
| Viscosity (after 5 min. at starting temperature 23°C) | app. 6.500 mPas |
| Pot Life at 5°C | app. 47 min. |
| at 23°C | app. 25 min. |
| at 35°C | app. 18 min. |
| Compound - Moulded Material | |
| Physical Structure | free of bubbles |
| Density (20°C) | 1,16 g/cm ³ |
| Hardness Shore A (23°C/7d) | app. 25 |